

Minerals

Application	
Market segment:	Glass / Ceramics
Material:	Kaolin powder, china clay
Feed size:	0-1 mm
Feed quantity:	100 g (+ 150 ml isopropanol)
Material specification(s):	Medium-hard, smeary
Customer requirment(s):	< 0.5 µm, research project
Subsequent analysis:	Colour Measurement
Solution	
Selected instrument(s):	Planetary Ball Mill
Configuration(s):	2 Grinding jars, 500 ml, Zirconia; per jar 300 ml grinding balls Zirconia Ø $$ 3 mm
Working settings:	320 rpm
Time:	5 h (per batch)
Time: Achieved result(s):	5 h (per batch) d50 = 1.4 μ m d90 = 6.3 μ m

LAARMANN® INNOVATORS IN SOLIDS



Kaolin

Application notes can only be used as a guideline. Each type material of has its own characteristics and therefore the outcome for each test may vary per material. We cannot accept any legal claims derived from this application note. This document is subjected to technical modification and errors.